



HSM Wire International, Inc

Ph: 330-244-8501 Fax: 330-244-8561

www.hsmwire.com



Alloy 120 - Precision Resistance

Chemical Composition

Nominal Composition	Fe%	Ni%	
	30	70	

Mechanical Properties

Melting Point	1,425°C (2,597°F)	Comments: Operating Temp
Max Operating Temp	1099°C (2010°F)	
Soft Tensile	70 - 100,000 PSI	
Elongation	15 - 30%	
Yield Point	40 - 60,000 PSI	
Tensile Strength at Break	483 MPa (70000 psi) 1030 MPa (150000 psi)	

Physical Properties

Ω /cir.mil.ft:	120
Conductivity:	28.9 / W/m-K (201 BTU-in/hr-ft ² -°F)
Coefficient of Linear Expansion , 10 ⁻⁶ :	15.0 μ m/m-°C @Temperature 20.0 °C 8.33 μ in/in-°F @Temperature 68.0 °F
Temp. coefficient of Resistance:	0.0045 ohms/ohm-°C Comments: 0-100°C
Weight/Density:	0.305 lbs/cu.in. (8.44 g/cc)
Specific Heat:	0.523 J/g-°C @Temperature 20.0 °C 0.125 BTU/lb-°F @Temperature 68.0 °F
Specific Gravity:	8.46

Electrical Properties

Electrical Resistivity	0.0000199 ohm-cm Comments: 3% tolerance on sizes below 0.02, 5% tolerance on sizes above 0.02
------------------------	---

*To be used as a guideline only.

Copyright ©2013 HSM Wire International

R1.06.04.2013



HSM Wire International, Inc

Ph: 330-244-8501 Fax: 330-244-8561

www.hsmwire.com



Resistance Chart

Diameter			Resistance @ 68°F/20°C Ω/ft	Sq. in/Ω	Weight	Ω/lb.	Ft/Lb	Cross Sectional area (in ²)
AWG	Inches	Mm		68°F	lb/1000 ft			
20	0.032	0.812	0.1171	9.800	2.94	39.78	339.7	0.000804
21	0.0285	0.723	0.1477	6.930	2.317	63.75	431.6	0.000638
22	0.0253	0.644	0.1860	4.850	1.825	101.9	547.9	0.000507
23	0.0226	0.573	0.2350	3.450	1.468	160.1	681.2	0.000401
24	0.0201	0.51	0.2970	2.430	1.15	258.3	869.6	0.000314
25	0.0179	0.455	0.3746	1.720	0.9201	396.3	1,087	0.000254
26	0.0159	0.405	0.4746	1.200	0.7262	653.5	1,377	0.000199
27	0.0142	0.361	0.5952	0.857	0.5797	1,027	1,725	0.000158
28	0.0126	0.321	0.7556	0.599	0.4585	1,648	2,181	0.000125
29	0.0113	0.286	0.9389	0.432	0.3606	2,606	2,773	0.000100
30	0.01	0.255	1.200	0.299	0.2873	4,177	3,481	0.0000785
31	0.0089	0.227	1.515	0.211	0.2276	6,657	4,394	0.0000626
32	0.008	0.202	1.875	0.153	0.1839	10,200	5,438	0.0000496
33	0.0071	0.18	2.38	0.107	0.1448	16,440	6,906	0.0000394
34	0.0063	0.16	3.022	0.075	0.114	26,510	8,772	0.0000312
35	0.0056	0.143	3.826	0.053	0.09011	42,090	11,000	0.0000247
36	0.005	0.127	4.80	0.0374	0.07184	66,820	13,920	0.0000196
37	0.0045	0.113	5.926	0.0273	0.02816	101,900	17,190	0.0000152
38	0.004	0.101	7.5	0.0206	0.04598	163,100	21,750	0.0000126
39	0.0035	0.09	9.796	0.0138	0.03517	278,500	28,430	0.00000979
40	0.0031	0.08	12.49	0.0096	0.027580	452,900	36,260	0.00000779
41	0.0028	0.07	15.86	0.0067	0.021720	730,342	46,029	0.00000616
42	0.0025	0.063	19.20	0.00503	0.01795	1,069,363	55,696	0.00000487

*To be used as a guideline only.

Copyright ©2013 HSM Wire International

R1.06.05.2013