



# HSM Wire International, Inc

Ph: 330-244-8501 Fax: 330-244-8561

www.hsmwire.com

## Tensile Strength of Cold Drawn Cr-Ni Stainless Steel Wire Diameter Range of 0.126 - 0.375"

AISI TYPE	TEMPER	YIELD-ksi	TENSILE-ksi	ELONG.%
<b>302</b>	1/4 hard	90-125	120-140	15-25
	1/2 hard	120-150	145-176	10-17
	3/4 hard	150-180	170-200	5-10
	*Full hard	180-220	190-230	2-5
<b>*Typical of wires used in making stranded wire rope</b>				
<b>304</b>	1/4 hard	90-110	120-140	20-30
	1/2 hard	120-140	130-170	10-18
	3/4 hard	140-170	170-200	5-10
	Full hard	170-210	200-240	2-5
<b>309S</b>	1/4 hard	80-90	110-130	15-25
	1/2 hard	105-125	125-155	10-11
	3/4 hard	125-150	140-180	8-12
	Full hard	150-185	160-190	4-8
<b>310S</b>	1/4 hard	80-90	110-130	15-25
	1/2 hard	105-125	125-155	10-11
	3/4 hard	125-150	140-180	8-12
	Full hard	150-185	160-195	3-6
<b>316</b>	1/4 hard	80-100	110-130	20-30
	1/2 hard	105-125	135-155	12-20
	3/4 hard	135-165	165-195	8-12
	Full hard	155-185	185-215	3-6
<b>321</b>	1/4 hard	90-110	120-140	20-30
	1/2 hard	120-140	150-170	10-18
	3/4 hard	140-170	170-200	5-10
	Full hard	170-210	200-240	2-5
<b>347</b>	1/4 hard	85-105	115-135	15-25
	1/2 hard	110-130	140-160	10-13
	3/4 hard	140-170	170-200	5-10
	Full hard	160-190	190-220	3-6