



# HSM Wire International, Inc

Ph: 330-244-8501 Fax: 330-244-8561

www.hsmwire.com



## Type I Non-Jacketed Wire Rope

MIL-DTL-83420, Latest Amendment Composition A, Carbon Steel, Tin or Zinc Coated

Part No.	Nominal Diameter		Construction	Allowable Increase of Dia. at Cut End		Min. Breaking Strength Comp. A		Tolerance on Diameter		Approx. Weight per 100 ft.	
	in.	mm		in.	mm	lbs.	kg.	in.	mm	lbs	kgs
<b>HSMG30</b>	1/32	0.79	3x7	0.006	0.152	110	50	0.006	0.152	0.16	0.07
<b>HSMG48</b>	3/64	1.19	7x7	0.008	0.203	270	122	0.008	0.203	0.42	0.19
<b>HSMG64</b>	1/16	1.59	7x7	0.009	0.229	480	218	0.010	0.254	0.75	0.34
<b>HSMG65</b>	1/16	1.59	7x19	0.009	0.229	480	218	0.010	0.254	0.75	0.34
<b>HSMG94</b>	3/32	2.38	7x7	0.010	0.254	920	418	0.012	0.305	1.60	0.72
<b>HSMG95</b>	3/32	2.38	7x19	0.010	0.254	1000	453	0.012	0.305	1.74	0.79
<b>HSMG126</b>	1/8	3.18	7x19	0.011	0.279	2000	907	0.014	0.356	2.90	1.31
<b>HSMG158</b>	5/32	3.97	7x19	0.017	0.432	2800	1270	0.016	0.406	4.50	2.04
<b>HSMG188</b>	3/16	4.76	7x19	0.019	0.483	4200	1905	0.018	0.457	6.50	2.95
<b>HSMG252</b>	1/4	6.35	7x19	0.021	0.533	7000	3175	0.018	0.457	11.00	4.99
<b>HSMG315</b>	5/16	7.94	7x19	0.024	0.610	9800	4445	0.022	0.559	17.30	7.85
<b>HSMG375</b>	3/8	9.53	7x19	0.027	0.686	14400	6532	0.026	0.660	24.30	11.00

To be used as a Guideline ONLY!

Copyright ©2013 HSM Wire International Inc.

R1. 08/11/2013